



IT-180ITC

High Tg/ Lead Free / Standard Loss Laminate & Prepreg

- Excellent CAF resistance
- Low CTE & Standard Loss performance
- High thermal reliability
- For high layer count PCB applications

Laminate properties

Items	IPC TM-650	Typical Value	Unit
Peel Strength, minimum			
A. Low profile copper foil	2.4.8	5-6	lb/inch
B. Standard profile copper foil		7-8	
Volume Resistivity	2.5.17.1	1x10 ¹⁰	MΩ-cm
Surface Resistivity	2.5.17.1	1x10 ¹⁰	MΩ
Moisture Absorption, maximum	2.6.2.1	0.12	%
Permittivity (Dk, 50% resin content)			
A. 1GHz		4.3	
B. 2GHz	2.5.5.13	4.1	--
C. 5GHz		4.0	
D. 10GHz		4.0	
Loss Tangent (Df, 50% resin content)			
A. 1GHz		0.013	
B. 2GHz	2.5.5.13	0.013	--
C. 5GHz		0.014	
D. 10GHz		0.015	
Flexural Strength, minimum			
A. Length direction	2.4.4	470-500	N/mm ²
B. Cross direction		420-450	
Thermal Stress 10 s at 288°C			
A. Unetched	2.4.13.1	Pass	Rating
B. Etched		Pass	
Flammability	UL94	V-0	Rating
Glass Transition Temperature(DSC)	2.4.25	175	°C
Decomposition Temperature	2.4.24.6	350	°C
X/Y Axis CTE (40°C to 125°C)	2.4.41	10-13	ppm/°C
Z-Axis CTE			
A. Alpha 1		40	ppm/°C
B. Alpha 2	2.4.24	210	ppm/°C
C. 50 to 260 Degrees C		2.3	%
Thermal Resistance			
A. T260	2.4.24.1	>60	Minutes
B. T288		>30	Minutes

